

**PRECATALYZED TOPCOAT LS
SERIES 5463
CLEAR**

DESCRIPTION:

5463 series is a pre-catalyzed synthetic lacquer where the catalyst is already incorporated to facilitate usage. 5463 series is used for the finishing of furniture, kitchen cabinets and other wood product. This lacquer has excellent transparency and dries quickly.

PRODUCT DATA:

PRODUCT CODE: 5463-0XX
 VISCOSITY (77°F): 21-24 sec (FC#4)
 SOLID % by Vol: 17.6 ± 1%
 SOLID % by WT: 24.4 ± 1%
 VOC AS APPLIED: 1.998 lbs/lbs solid
 VOC: 440.5 g/L
 VOC: 3.66 lbs/gal
 HAPS AS APPLIED: 0.597 lbs/lbs solid
 DENSITY: 7.557 lbs/gal
 SHEEN: 10°, 20°, 35°, 50°, 90°
 SHELF LIFE: 8 months

MIXING RATIO:

THINNER: 5400-050 (0-10%)
 RETARDER: 400-068 (0-5%)
 400-025 (0-5%)

DRYING TIMES:

THICKNESS APPLIED: 3 wet mils
 DUST FREE: 5-7 minutes
 READY TO HANDLE: 15-20 minutes
 READY TO PACK: Next day

Note: Drying times may vary depending on thickness applied, temperature and/or humidity.

Warning: Total film thickness of the finish should not exceed 5 mils dry film.

APPLICATION:

Surfaces should be clean, oil free, grease free and well sanded (grit #320 - #400). Ensure product is stirred thoroughly and mixed according to specifications before applying. Avoid thick coats.

CONVENTIONAL EQUIPMENT:

VISCOSITY: 21-22 sec (FC#4)
 TANK PRESSURE: 15-18 PSI
 AIR PRESSURE: 35-45 PSI

AIR MIX EQUIPMENT:

ATOMISATION: 15-25 PSI
 MATERIAL PRESSURE: 40-50 PSI (20:1 ratio)
 TIP: 09
 NUMBER OF COATS: 1-2

AIRLESS EQUIPMENT:

VISCOSITY: 21-22 sec (FC#4)
 GUN PRESSURE: 900-1100 PSI
 NUMBER OF COATS: 1-2

STORAGE:

Store in a dry and cool area. Close the container properly after use.

The customer is responsible for following the recommended application procedures. Failure to adhere to these specifications may result in poor appearance or failure of film. This product is for professional use only. Consult your local representative before applying with other manufacturer products. The customers should test the complete system for adhesion, compatibility and performance prior to full scale application. Please refer to the Material Safety Data Sheet (MSDS) for safety information and cautions prior to using this product. We ONLY guarantee our product to conform to our quality. Our responsibility as manufacturer is limited to the cost of the product. Please feel free to contact us at (819) 367-2201 for any further inquiries regarding this product. All information on this product data sheet is subject to change without notice.