

**POLYESTER SEALER
SERIES J110
CLEAR**

DESCRIPTION:

The J110 is a three-component polyester sanding sealer from the Verinlegno series. It can be used for the finishing of flat panels, kitchen doors, moulding and all other components fabricated from wood and MDF. This product has excellent filling properties for open grain species and exotics wood. It is very clear and has excellent sanding properties.

PRODUCT DATA:

PRODUCT CODE	J110
VISCOSITY (77°F):	160 ± 2 sec (FC#4)
VISCOSITY:	20 ± 2 sec (FC#4) (at application)
SOLID % by WT:	92 ± 2%
SOLID % by WT:	80-85 ± 2% (at application)
VOC AS APPLIED:	X lbs/lbs solid
VOC:	X g/L
VOC:	X lbs/gal
HAPS AS APPLIED:	X lbs/lbs solid
DENSITY:	8.466 lbs/gal
SHELF LIFE:	12 months

MIXING RATIO:

PRODUCT FORMULATION	
J110 POLYESTER:	1 part
J910 COBALT:	2% by volume or weight
REDUCER:	5400-037 (10-20%)
J930 PEROXIDE:	2% by volume or weight
POT LIFE:	3 hours max at 68°F

DRYING TIMES:

THICKNESS APPLIED:	6-7 wet mils
READY TO HANDLE:	2 hours
READY TO STACK:	8 hours
READY TO SAND:	24 hours

Note: Drying times may vary depending on thickness applied, temperature and/or humidity.

Warning: It is not recommended to use a product whose pot life has expired.

Recoat: Must be done within 35 to 40 minutes when doing wet application (recommended).

APPLICATION:

Substrate should be well sanded and free of any traces of dust, oil or grease. Before application ensure that both products are thoroughly mixed together. First J910 cobalt, second acetone, third J930 peroxide.

APPLICATION EQUIPMENT:

SPRAY GUN	
PRESSURE TANK	
TWO COMPONENT POMP	
FINISH THICKNESS:	6-7 wet mils
NUMBER OF COATS:	2 to 4

TYPICAL SYSTEM:

TP WIPING STAIN	
A170 ISOLANTE:	1 coat 2 wet mils
J110 POLYESTER:	2-4 coats 6-7 wet mils each coat
I600 TOPCOAT HG:	1-2 coats 4-5 wet mils each coat
NUMBER OF COATS:	1-2 coats

STORAGE:

Store in a dry and cool area. Close the container properly after use.

The customer is responsible for following the recommended application procedures. Failure to adhere to these specifications may result in poor appearance or failure of film. This product is for professional use only. Consult your local representative before applying with other manufacturer products. The customers should test the complete system for adhesion, compatibility and performance prior to full scale application. Please refer to the Material Safety Data Sheet (MSDS) for safety information and cautions prior to using this product. We ONLY guarantee our product to conform to our quality. Our responsibility as manufacturer is limited to the cost of the product. Please feel free to contact us at (819) 367-2201 for any further inquiries regarding this product. All information on this product data sheet is subject to change without notice.